

Vidoflex HT

Property	Value	Test method
Temperature range (°c)	+150 - 0	
Density (kg/m ³)	10 ± 85	
Thermal conductivity λ W/(m*k)	10°C 0.0388 W / (m*k)	EN12667 or EN12939 for flat EN ISO 13787 for tubes
Ozone resistance	No cracks	ASTM D 1171
U.V. resistance	No cracks	ASTM G 154
Water absorption	kg/m ² 1 >	En 12086 For sheet & rolls En 13469 For tubes
Dimensional stability	Thickness Δε<3.0% Length & width Δε <2.0%	EN 1604
Fier behavior	B2	DIN 4102
CFC content	CFC & HCFC free	SFS 4190 Class 1