

## Vidoflex EXTRA PLUS

Property	Value	Test method
Temperature range (°C)	+125 - 40(-)	
Density (kg/m <sup>3</sup> )	75 - 55	
Thermal conductivity λ W/(m*k)	0°C 0.037 40°C 0.040 <b>W / (m*k)</b>	EN ISO 13787 for tubes
Water vapour diffusion resistance	μ ≥10,000	EN 13469
Ozone resistance	No cracks	ASTM D 1171
U.V. resistance	No cracks	ASTM G 154
Water absorption	< 0.1 kg/m <sup>2</sup>	En 13469 For tubes
Dimensional stability	Thickness Δε<3.0% Length & width Δε <2.0%	EN 1604
Fire behavior	Class 1 Class 0 V ; 3 ; 3	BS 476 Part 7 BS 476 Part 6 &7 IIS 755 י"ת
CFC content	CFC & HCFC free	SFS 4190 Class 1